



H²OLOTM
RUBBERPAVE+

Typical properties	Air voids	Water sensitivity	Stiffness	Wheel tracking	
Standard	BS EN 12697-8	BS EN 12697-12	BS EN 12697-26	BS EN 12697-22 Procedure B at 60°C	
	%	ITSR	ITSM	WTS _{AIR}	PRD _{AIR}
10mm SMA 10 rubber modified	3%	90%	3200MPa	0.20	10%
10mm SMA 40/60 pen	4%	80%	3400MPa	0.20	10%
AC close graded 100/150 pen	8%	80%	1300MPa	0.80	27%